# TECHNICAL INFO



**Liquid Coatings Sheet** 

TILC/T-2.1122

# **High Temperature Liquid**

# **General Description**

High Temperature Liquid is a high quality, flat finish pure silicone alkyd, designed to resist temperatures up to 1200°F (649°C). This coating is formulated to provide long-term protection.

#### **Typical Uses**

As an economy coating for use directly over the properly prepared surfaces for indoor and outdoor chemical and refinery installations, diesel generator exhaust, bake oven applications, foundries, and special applications in the aircraft and space industries where the following attributes are desirable:

- Good hide and coverage
- Long-term protection
- Resists heat up to 1200°F (649°C)

### **Compatibility with Other Coatings**

Not compatible with the use of a primer.

#### **Not Recommended For**

- Immersion service in potable water, chemicals or hydrocarbons
- Extreme UV exposure without topcoat

#### Color

982 Black 983 Aluminum

# **Application**

#### **Surface Preparation**

BARE FERROUS METAL: Clean off all dirt, grease, oil, wax or other foreign matter. All loose, powdery or scaling rust must also be removed. A completely de-rusted surface is recommended. All surfaces should be cleaned with solvent (SSPC-SP1) to remove any grease or oil contaminants prior to painting.

# **Physical Properties of the Coating**

Volume Solids:
Weight Solids:
Solvents Used:
Flash Point:

Gloss: Low glo Recommended DFT: 2.0 - 3.0

Application by spray only.

Aliphatic Hydrocarbon / Ketones 40°F (4.4°C) PMCC

Low gloss

25% ± 2%

40% ± 2%

2.0 - 3.0 mils DFT (6.0 - 10.0 mils WFT)

# Safety and Handling

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation and gloves.

TO AVOID SPONTANEOUS COMBUSTION, SOAKED SOILED RAGS, SPRAY BOOTH FILTERS, OVERSPRAY WASTE AND DRY DUST SWEEPINGS MUST BE PROPERLY DISCARDED IN WATER FILLED CONTAINERS AND DISPOSED OF IN ACCORDANCE WITH LOCAL DISPOSAL REGULATIONS.

All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable and are intended for professional use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.

## **Disclaimer**

Conditions under which our materials may be used are beyond our control. The suitability for application and performance of finished goods coated with Twin City Fan material is the sole responsibility of the customer and end user. Twin City Fan expressly denies specific or implied warranties including warranties for fitness for a particular use or purpose.



TWIN CITY FAN & BLOWER | WWW.TCF.COM